

## Product Description

**Inplex 2163** is a calcium sulphonate grease designed for heavy duty use. It provides excellent lubrication in steel and paper making machinery and many other heavy industrial applications.

## Product Features & Benefits

**Inplex 2163** contains no heavy metals or other harmful or environmentally undesirable additives such as sulphur, phosphorus, chlorine, zinc, phenols, antimony, barium or lead.

## Application:

Inplex 2163 is suitable for use in automotive, industrial, construction, agriculture, railroad, and mining operations.

Specific applications include:

- All chassis points for automotive
- Fifth wheels
- King pins
- Anti-friction bearings
- Low and high speed journal bearings
- Oven conveyors, electric motor bearings, steel mill roller bearings
- On farm and earth moving equipment
- Severe industrial applications such as pulp, steel mills

Inplex 2163 is also excellent for use in marine type applications where water washout and corrosion are of primary concern.

The benefits of Inplex 2163 are:

- Outstanding mechanical ability
- Excellent load carrying ability
- Excellent thermal stability
- Excellent oxidation stability
- Excellent resistance to water
- Very good water washout
- Excellent corrosion resistance

## Additional Information

Inplex 2163 is a calcium sulphonate grease designed for heavy duty use. It provides excellent lubrication in steel and paper making machinery and many other heavy industrial applications.

Calcium Sulphonate greases are technically advanced premium greases characterised by exceptional mechanical stability, excellent resistance to rust and corrosion and very high heat and load carrying capabilities.

Physical Results for NLGI-2 Grade		
Test	Method	Results
Colours	Visual	Tan
Texture	Visual	Smooth
Dropping Point, °C	ATSM D2265	318
Consistency, 60 strokes, mm/10	ASTM D217	280
Mechanical Stability Worked 10,000 Strokes, % change Worked 10,000 Strokes, with 50/50 water, %	ASTM217	2.3 8.0 8.0
Timken OK Load, kg 4-Ball EP LWI, kgf Weld Point, kg	ASTM D2509 ASTM D2596	27.2 62 500
4-Ball Wear, mm	ASTM D 2266	0.04
Rust Test rating	ASTM D1743	Pass
Salt Fog Corrosion, 1 mil d.f.t, hours	ASTM B117	>300
Copper Corrosion, rating	ASTM D4048	1B
Wheel Bearing Leakage, grams	ASTM D4290	4.0
Bearing Life Performance, hours	ASTM D3527	160
Bomb Oxidation, psi drop after 1000 hours	ASTM D942	9.0
Water Washout at 80 °C, % lost	ASTM D1264	1.0
Resistance to Water Spray, % retained	ASTM D4049	80
Oil Separation, % loss	ASTM D1742	0.2
Mobility @ -18 °C, g/minute	US Steel Method	5.5

The values quoted above are typical of normal production. They do not constitute a specification.

Physical Results for NLGI-3 Grade		
Test	Method	Results
Colours	Visual	Tan
Texture	Visual	Smooth
Worked Penetration, 25 °C, 60 Strokes 10,000 Strokes change from 60 Strokes 100,000 Strokes change from 60 Strokes	ASTM D 217	240 ±1 ±2
Dropping Point, °C	ATSM D 2265	300
Rust Prevention	ASTM D 1743	Pass
Oxidation Stability, PSI Loss, 100 hours 500 hours 1,000 hours	ASTM D 942	0 2 9
Roll Stability, Penetration Change	ASTM D 1831	+2
Oil Separation, 24 hours @ 25 °C	ASTM D 1742	0.17
Four Ball EP, Weld Point, kg	ASTM D 2596	500
Four Ball EP, Load Wear Index, kg	ASTM D 2596	65
Four Ball Wear, Scar mm	ASTM D 2266	0.39
Timken OK Load, kg	ASTM D 2509	29.4
Salt Fog, hours	ASTM B 117	4000
Water Washout, % loss		2.75
Wheel Bearing Leakage, % loss, gms	ASTM D 1263	0.4
Fretting Wear Protection, mgs loss Ambient Temperature @-17.7 °F	ASTM D 4170	2.50 6.20
<b>Base Oil Characteristics</b>		
Viscosities: @ 100 °C, cSt @ 40 °C, cSt		16.5 233
Viscosity Index		95
Pour Point, °C		-17.7

The values quoted above are typical of normal production. They do not constitute a specification.

Master Item# 1813 & 1815

Pack Size Availability: NLGI 2:450g, 2.5kg, 20kg, 180kg

NLGI 3: 20kg, 180kg

Last Updated: 21<sup>st</sup> December 2021