



FREQUENTLY ASKED QUESTIONS:

Q. Can I use *Epoxy Floor Coating* on my carport, driveway, or pool deck?

A. No, *Epoxy Floor Coating* is designed for **INTERIOR USE ONLY**.

Q. Can I use *Epoxy Floor Coating* on a previously coated floor?

A. The coating will need to be fully removed prior to the application of *Epoxy Floor Coating*.

Q. Can I apply *Epoxy Floor Coating* to new concrete?

A. Allow newly poured concrete to cure for a minimum of 4 weeks prior to coating. All new concrete floors need to be acid etched before the application of *Epoxy Floor Coating*.

Q. Do I need to fill cracks in my concrete?

A. Yes. This will ensure uniform application as well as improving surface appearance and longevity.

Q. How large an area will the kit cover?

A. A single 8-litre kit will cover a standard double garage approximately (36–40 sqm) with one coat.

Q. How many coats are required?

A. Only 1 coat is necessary under most circumstances. However, for weathered, discolored, rough, or porous concrete, a second coat may be required. (Which will require the purchase of a second kit).

Q. How long will the project take?

A. The project may be completed over 2 weekends depending on temperature conditions and the drying time of the etched/washed concrete.

Q. How do I remove spills from my coated floor?

A. Spills can be wiped up easily with an absorbent cloth.

Q. What are the dry times for *Epoxy Floor Coating*?

A. Dry times will vary according to the ambient temperature. (Please refer to Dry Times table in the Instruction Manual).

Q. Why do I need to let the coating stand after mixing the 2 parts together?

A. The standing time allows the epoxy product to activate fully.



Q. What are the decorative chips made of?

A. Vinyl.

Q. Can tyre marks be removed from my coated floor?

A. Yes. Tyre marks can be wiped off.

Q. Will hot tyres cause the coating to lift up from the floor?

A. No. *Epoxy Floor Coating* has been designed to resist hot tyre pick-up. (Subject to suitability of concrete floor, correct preparation, and application).

Q. How long should the garage door be left open after application?

A. Keep the garage door open for at least 5–6 hours. This will assist with the drying process and allow for adequate ventilation during the curing process.

Q. How do I clean up?

A. Dispose of rollers and brushes used to apply *Epoxy Floor Coating*. Clean up tools, equipment, and spills **IMMEDIATELY** with Xylene, as dried epoxy is very difficult to remove. Allow leftover epoxy to harden in the container and dispose of it according to council/regional regulations.

Q. Are the coatings slippery?

A. The coating is not slippery when dry. However, the coated surface may become slippery when wet or exposed to oils and grease.