

PLASTIC STEEL® 5-MINUTE® PUTTY (SF)

DESCRIPTION

A steel-filled, fast-setting epoxy putty for filling, rebuilding, and bonding metal surfaces.



INTENDED USE

Industrial Use: Restores worn or fatigued metals; patches castings; makes jigs and fixtures; rebuilds pump and valve bodies; restores bearing journals and races.

PRODUCT FEATURES

- Bonds to aluminum, concrete, and many other metals
- Resistant to chemicals and most acids, bases, solvents, and alkalis
- Applies easily to vertical surfaces
- Machinable to metallic finish

LIMITATIONS

Suitability of product is determined by the end user for their application and process.
Not recommended for long term exposure to concentrated acids or to organic solvents.

TYPICAL PHYSICAL PROPERTIES

Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Adhesive Tensile Shear	2,026 psi (14.0 MPa)	Cure Shrinkage ASTM D 2566
Coefficient of Thermal Expansion (x10 ⁻⁶)	34 in/in.°F (61.2 cm/cm.°C)	Adhesive Tensile Shear ASTM D 1002
Compression Strength	10,400 psi (71.7 MPa)	Dielectric Strength, volts/mil ASTM D 149
Cured Shrinkage	0.0006 in/in (cm/cm)	Coef. of Thermal Expansion ASTM D 696
Dielectric Constant	35	Flexural Strength ASTM D 790
Dielectric Strength	30 volts/mil (1.2 kV/mm)	Thermal Conductivity ASTM C 177
Flexural Strength	7,680 psi (52.9 MPa)	Compressive Strength ASTM D 695
Hardness	85 Shore D	Cured Hardness Shore D ASTM D 2240
Modulus of Elasticity	7.5 psi x10 ⁵ (5.2 GPa)	Dielectric Constant ASTM D 150
Solids by Volume	100%	Modulus of Elasticity ASTM D 638
Temperature Resistance	Dry: 200°F (93°C)	
Thermal Conductivity (x10 ⁻³)	2.65 cal/s.cm.°C	

Uncured Properties @ 72°F (23°C)	Typical Values
Color	Dark Grey
Coverage (1/4" / 6.35mm)	49 in ² /lb (697 cm ² /Kg)
Functional Cure	1 hr
Mix Ratio by Volume	1:01
Mix Ratio by Weight	1.7:1
Mixed Viscosity	Putty
Pot Life @ 75F	5 min.
Recoat Time	15-30 min.
Specific Gravity	2.2
Specific Volume	12.2 in ³ /lb (0.44 cm ³ /g)

SURFACE PREPARATION

1. Thoroughly clean the surface with a solvent such as Isopropanol Alcohol or Acetone to remove all oil, grease and dirt.
2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white metal is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40ppm).

3. Clean surface again with a solvent such as Isopropanol Alcohol or Acetone to remove all traces of oil, grease, dust or other foreign substances from the grit blasting.
4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55°F to 90°F (13°C to 32°C). In cold working conditions, directly heat repair area to 100 - 110°F (38°C - 43°C) prior to applying epoxy and maintain at this temperature during any moisture, product cure to dry off contamination or solvents, as well as to achieve maximum performance properties.

MIXING INSTRUCTIONS

---- It is strongly recommended that full units be mixed, as ratios are pre-measured. ----

1. Add hardener to resin.
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of container) until a uniform, streak-free consistency is obtained.

INTERMEDIATE SIZES (1,2,3 lb. units): Place resin and hardener on a flat, disposable surface such as cardboard, plywood or plastic sheet. Use a trowel or wide-blade tool to mix the material as in Step 2 above.

LARGE SIZES: (25 lb., 30 lb., 50 lb. buckets): Use a T-shaped mixing paddle or a propeller-type Jiffy Mixer Model ES on an electric drill. Thoroughly fold putty by vigorously moving paddle/propeller up and down until a homogenous mix of resin and hardener is attained.

APPLICATION INSTRUCTIONS

1. Spread mixed material on repair area and work firmly into substrate to ensure maximum surface contact.
2. Assemble with mating part within recommended working time.
3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet of epoxy should flow out the edges to display adequate gap fill.) Plastic Steel® 5-Minute® Putty (SF) fully cures in 16 hours, at which time it can be machined, drilled, or painted.

FOR BRIDGING LARGE GAPS OR HOLES

Place fiberglass sheet, expanded metal, or mechanical fasteners between repair area and Plastic Steel® 5 Minute® Putty (SF) prior to application.

FOR VERTICAL SURFACE APPLICATIONS

Plastic Steel® 5 Minute® Putty (SF) can be troweled up to 1/4" (6.4 mm) thick without sagging.

FOR MAXIMUM PHYSICAL PROPERTIES

Cure at room temperature for 2.5 hours, then heat cure for 4 hours @ 200°F (93°C)

FOR ± 70°F APPLICATIONS

Applying epoxy at temperatures below 70°F (21°C) lengthens functional cure and pot lifetimes. Conversely, applying above 70°F (21°C) shortens functional cure and pot life.

MACHINING:

Allow material to cure for at least one hour before machining.

- Lathe speed: 150 ft/min
- Cut: Dry
- Tools: Carbide Top Rake 6° (+/-2°) – Side/Front 8°F (+/-2°)
- Feed Rate (rough): Travel speed .020 Rough cut .020 - .060
- Feed Rate (finishing): Travel speed .010 Finish cut .010
- Polishing: Use 400-650 grit emery paper wet. Material should polish to a 25-50 micro inch.

STORAGE

Shelf life 3 yrs from manufacture. See package label. Store at room temperature, 70 °F (21°C).

CHEMICAL RESISTANCE

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F (24°C)

1,1,1-Trichloroethane	Fair
Ammonium Hydroxide 20%	Fair
Cutting Oil	Very good
Gasoline (Unleaded)	Very good
Hydrochloric 10%	Fair
Methyl Ethyl Ketone	Poor
Methylene Chloride	Poor
Mineral Spirits	Very good

Phosphoric 10%	Fair
Potassium Hydroxide 20%	Fair
Sodium Chloride Brine	Fair
Sodium Hypochlorite	Fair
Sulfuric 10%	Fair
Sulfuric 50%	Poor
Trisodium Phosphate	Fair
Xylene	Fair

PRECAUTIONS

FOR INDUSTRIAL USE ONLY: Please refer to the appropriate **S**afety **D**ata **S**heet prior to using this product.

WARRANTY

ITW Polymers & Fluids will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

ORDER INFORMATION

Item No.	Package Size
D10240	600gm
D10250	250gm

CONTACTS

ITW Polymers & Fluids
100 Hassall St Wetherill Park
NSW 2164 Australia
AU Phone: 1800 000 945
itwpf.com.au

ITW Polymers & Fluids
Unit 2 / 38 Trugood Drive
East Tamaki, 2013, Auckland, New Zealand
NZ Phone: 0800 476 265
itwpf.co.nz

EMERGENCY:
AU: 1800 033 111
NZ: 0800 734 607

DISCLAIMER

All information on this data sheet is based on laboratory testing and is not intended for design purposes.
ITW Polymers & Fluids and Devcon® makes no representations or warranties of any kind concerning this data.